

iQ Granit SD

Datasheet

	Norm	iQ Granit SD 2.0 mm (2022 renewal)	iQ Granit SD Tiles 2.0 mm (2022 renewal)
Classification			
Product type	ISO 10581	Static dissipative pressed homogeneous vinyl flooring	
Binder content	ISO 10581	Type I	
Commercial classification	ISO 10874	34 Very Heavy	
Industrial classification	ISO 10874	43 Heavy	
Technical Characteristics			
Surface treatment		New iQ PUR	
Surface Restoration		Yes	
Total thickness	ISO 24346	2 mm	
Wear layer thickness	ISO 24340	2 mm	
Total weight	ISO 23997	2800 g/m ²	
Performance for CE Marking			
Declaration of Performance #	EN 14041	0019-0033-DoP-2013-07	
Reaction to fire	EN 13501-1	Bfl-s1	
Reaction to fire	EN ISO 9239-1	≥ 8 kW/m ²	
Reaction to fire - EN ISO 11925-2	EN ISO 11925-2	Pass	
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)	
Thermal resistance	EN 12667	~0,010 m ² ·K/W	
Slip resistance (EN 13893)	EN 13893	Class DS (μ ≥ 0,30)	
Technical Performance			
Residual indentation	EN ISO 24343-1	Best measured value: 0,02 mm ≤ 0,10 mm	
Slip resistance	DIN 51130	R9	
Slip Resistance (EN 16165 Annex C)	BS 7976-2	Low risk of slip	
Electrical Insulation	VDE0100, Part 600	Ri ≥ 5x10 ⁴ Ohms	
Electrical resistance	ESD-approval SP method 2472	R ≤ 10 ⁹ Ohms	
Electrical resistance	EN 1081	R1 ≤ 10 ⁸ Ohms / R2 ≤ 10 ⁸ Ohms	
Electrical Resistance	EN/IEC 61340-4-1, 100 V	R ≤ 10 ⁸ Ohms*	
Curl resultant to heat	EN ISO 23999	≤ 8 mm for rolls	≤ 2 mm for tiles
Clean room	ISO 14644-1	ISO class 4	
Castor chair	ISO 4918	Suitable	
Light fastness	ISO 105-B02	≥ 7	
Dimensional stability	EN ISO 23999	Average Measured Value : ≤ 0.40 %	Average measured value : ≤ 0.25 % for tiles
Ease of Decontamination	ISO 8690 – DIN 25415	Excellent	
Chemical resistance	ISO 26987	Excellent Resistance	
Bacteria Resistance	ISO 846 Part C	Does not promote growth	
Underfloor heating		Suitable (subfloor temperature maximum 27°C)	
Seam Strength Average Value	EN 684	≥ 240 N/50mm	
Seam Strength Individual Value	EN 684	≥ 180 N/50mm	
Sustainability performances			
Recyclability through ReStart®		Offcuts / Post-use - Contact Tarkett for more information	
Recycled content		25,5 %	
Carbon Footprint (Cradle-to-Gate, EPD Modules A1 -A3)		3,48 kg CO ₂ eq /m ²	
Total Carbon Footprint (EPD Modules A-D, incl. recycling scenario)		1,81 kg CO ₂ eq /m ²	
Total VOC Emissions (after 28 days)	EN 16516	Platinum (≤ 10 µg/m ³)	
Formaldehyde emission		E1	
Dimensions and designs			
Roll		Roll 2 x 23 m	
Tile			Tile 610 x 610 mm - 14 tiles=5,2 m ² /box - 40 boxes/pallet
Number of designs available		14	14

* Measured to ground



The above information is subject to modification for the benefit of further improvement (04/03/2026). According to the European Regulation N°305/2011, for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.

