

Professional (22 mm)

Datasheet



INSTALLATION

- Installation method: On joists, glue down or floating
- Installation instruction: Download from www.tarkett.com. Contact your supplier for more details
- Underfloor heating compatible. Maximum floor surface temperature 27°C with self-regulating underfloor heating system
- Start & Stop: Shorter lengths of planks included in approx. 1 pack per 20 m²

MAINTENANCE

These Tarkett wooden floors have a Proteco surface treatment and therefore a strong protection against normal wear, abrasion, scratches and stains. Some floors will require more frequent maintenance for increased life span. Generally these products are light coloured floors and hardwax oiled floors, particularly with brushed surface and/or highlighted details.

Always make sure to follow the most recently updated maintenance instructions on www.tarkett.com.

RECOMMENDED ACCESSORIES

- Installation: Tarkofoam II / Tarkoflex II / Installation kit
- Aesthetics: Skirting, Pipe covers
- Care & maintenance: Tarkoclean for lacquered floors, Refresher for lacquered floors

See more alternatives and the complete range of accessories @ www.tarkett.com

Product Name	Product Code	Page
Professional (22 mm) - OAK NATURE TRES (3-strip)	7825012	3

Professional (22 mm) - OAK NATURE TRES (3-strip)

Datasheet

Product Information	Tarkett Value
Material code	7825012
Format	Plank 194 x 2535 mm
Pattern	(3-strip)
Surface treatment	Proteco Natura
Surface effect	None
Wear layer thickness	3,5 mm
Total thickness	22 mm
Items per box	4
Surface per box	1,97 m ²
Surface per pallet	68,95 m ²
Net weight	11,7 kg
Character	Calm
Latin Name	Quercus Robur & Quercus Petraea
Declaration of Performance #	0020-0117
EPD Number	EPD-IES-0026264
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)	-10,557 kg CO ₂ eq /m ²
LRV - overall average / Standard deviation	26 / 4

Due to the nature of the material this table shows typical values.

Characteristics & Technical Performance	Tarkett Value	Norm
Reaction to fire	Dfl-s1	EN 14342 - Table 1
Formaldehyde emission	E1	EN 14342
Brinell hardness (average value)	3.7	(BHN) EN 1534
Thermal insulation value : board only (RT m2 K/W)	0.152	EN ISO 10456:2007
Thermal insulation value : with rag felt (RT m2 K/W)	0.182	EN ISO 10456:2007
Thermal insulation value : with 2 mm Tarkofoam/flex II (RT m2 K/W)	0.192	EN ISO 10456:2007
Thermal conductivity (W/m K)	0.136	EN 12664 / EN 14342:2013
Taber Abraser/Lacquer's wear resistance	3500	EN 13696
Slip Resistance (EN 16165 Annex C)	Low risk of slip	BS 7976-2
Construction	Softwood Veneer and Lamella core 3-layer	



The quality of monitor and printer and the nature of wood results in variations in the colour and structure of individual planks.

